



INDUSTRIAL SOLUTIONS INTERNATIONAL
Technical Office

Product Data Sheet

Product	Dybond Easiflow Cement
Product Base	Chrome air setting mortar
Application	Jointing of magnesia chrome bricks
Chemical Analysis (%)	
SiO ₂	4.7
Fe ₂ O ₃	27.5
Al ₂ O ₃	15.0
Cr ₂ O ₃	43.6
CaO	0.20
MgO	9.3
Grain Size (mm)	0 – 0.1
Water Addition (%)	15 - 20
Use	Use within 1 hour of mixing

Date of Issue October 25, 2007

Version ZMCKA-19-11-2007

The data presented are typical, and not contractual conditions of acceptance. The data presented are average values obtained by laboratory testing of production volumes. The extent and frequency of such testing is defined by the internal procedures of the Quality Management System according to EN ISO 9001:2000 standard.

All rights are reserved to make modifications and updates to the presented data.